

# 

<b>Technical Report:</b> Date Received: Mod. Date:	( <b>6623</b> ) <b>136-***</b> APR. 03,2023		MAY.16, 2 Page 1	
	D,HESHAN TOWN,TONGXIANG			
CITY,JIAXING CITY,Z	CHEJIANG PROVINCE			
Sample Description:	POLYPROPYLENE FIBER			
Manufacturer:	/	PO No.:	/	
Buyer:	/	Style:	18176	
Country of Origin:	/	Country of Destination:	/	
Color:	/	SKU:	/	
Protocol No.:	/	Previous Report No.:	/	

TEST REQUESTED	CONCLUSION	Remark
1) COLORFASTNESS TO LIGHT-AATCC 16.3	PASS	-

### **REMARK:**

The client specifies the test methods and requirements.

\*\*\*\*\*\*\* TEXTILE CO.,LTD

Technical Report: (6623)136-\*\*\*\*

MAÝ.16, 2023 Page 2 of 3

# BVCPS (SHANGHAI) GENERAL CONTACT INFORMATION FOR THIS REPORT

TELEPHONE NO 86-21-24166888

E-MAIL: bvcpshltoy.sh@cn.bureauveritas.com

**BUREAU VERITAS** 

CONSUMER PRODUCTS SERVICE DIVISION (SHANGHAI)

**Laboratory Test location:** 

No. 368, Guangzhong Road, Zhuanqiao Town, Minhang, Shanghai. No. 168, Guanghua Road, Zhuanqiao Town, Minhang, Shanghai.

Hyde Bao

PRODUCT LINE MANAGER(HARDLINE DIVISION)

\*\*\*\*\*\*\*\*\*\*\* TEXTILE CO.,LTD Technical Report: (6623)136-\*\*\*\*

MAY.16, 2023

Page 3 of 3

# TEST RESULT

COLORFASTNESS TO LIGHT (AATCC 16.3:2020 OPTION 3 1000 AFU)				
	TEST ITEM 1:Blue fabric	REQUIREMENT		
COLOR CHANGE	Grade 4.5	MIN. GRADE 4		
CONCLUSION	PASS			

# **COLOURFASTNESS RATING**


Grade 5 negligible or no change or staining

Grade 4 slightly changed or stained

Grade 3 noticeably changed or stained

Grade 2 considerably changed or stained

Grade 1 much changed or stained



**EXHIBIT** 

